

## Steel grade

|  |  |
|--|--|
| Material No. / Werkstoff-Nr.                                   | PREMIUM 1.6582   |
| Description  | 34CrNiMo6  |
| AISI/SAE   | 4337   |
| Search for alternatives in the ABRAMS STEEL GUIDE <sup>®</sup> | <a href="http://www.steel-guide.eu/alternatives/4337">www.steel-guide.eu/alternatives/4337</a> |

## Specifications



**Round steel [RS]**  
black  
L: 500 mm  
L: 1.000 mm

## Chemical composition AISI/SAE 4337 (reference value %)

| C           | Si      | Mn        | P         | S         | Cr        | Mo          | Ni        |
|-------------|---------|-----------|-----------|-----------|-----------|-------------|-----------|
| 0,15 - 0,21 | 0 - 0,4 | 0,5 - 0,9 | 0 - 0,025 | 0 - 0,035 | 1,5 - 1,8 | 0,25 - 0,35 | 1,4 - 1,7 |

## Physical properties

|  |                                |            |            |            |
|--|--------------------------------|------------|------------|------------|
| Hardness (delivery condition)                            | max. 352 HB, tempered          |            |            |            |
| Tensile strength R <sub>m</sub> (as received condition)  | approx. 1200 N/mm <sup>2</sup> |            |            |            |
| Working hardness   | max. 38 HRC                    |            |            |            |
| Thermal expansion coefficient 10 <sup>-6</sup> m/(m • K) | 20 - 100°C                     | 20 - 200°C | 20 - 300°C | 20 - 400°C |
|  | 11,1                           | 12,1       | 12,9       | 13,5       |
| Thermal conductivity W/(m • K)                           | 20°C                           |            |            |            |
|  | 42,6                           |            |            |            |

## Technical properties

CrNiMo alloyed heat-treatable steel (tempered condition) for components with high strength and toughness. It is used for through-hardening components in automotive and mechanical engineering. The material is usually difficult to weld. Components are usually used in the quenched and tempered state. An optionally achievable surface hardness through nitriding: approx. 58-62HRC.

## Applications


Shafts, gear parts, gears, bevel gears, driving pinion.

## Heat treatment


|                  | Temperature | Cooling                  | Hardness    |
|------------------|-------------|--------------------------|-------------|
| Normal annealing | 850 - 880°C | Air                      | max. 248 HB |
| Soft annealing   | Temperature | Cooling                  |             |
|                  | 650 - 700°C | Furnace                  |             |
| Hardening        | Temperature | Quenching in             |             |
|                  | 830 - 860°C | Oil, polymer, water, air |             |



## Continuous ZTU-diagram



## Hardenability scatter band



## Hardening and tempering diagram

